



Thermal
Fire
Corrosion

Call us for more information at 604-576-2212

FIREX-FS II - Clear Exterior/Interior Wood Fire Retardant

APPLICATION INSTRUCTIONS

Application: FS II should be applied as is by spraying or immersing. Use low pressure spray equipment, brush or roll. Apply at the rate of 125 sq. ft. per gallon or 12.83 mils WFT. If spraying on a vertical surface where runoff could occur, multiple applications are required, wait until the first coat has penetrated (1-2 hrs.) and begin next application. One coat is considered cured after a 24 hour period. The only time that multiple coats may be required is on woods that have a moisture content below 8% or if runoff is an issue. To obtain a Class A rating the entire coverage rate of 125 sq. ft. per gallon must be applied to wood with no runoff.